

MECHANICAL PROPERTIES OF METAL MATRIX COMPOSITES UNDER DYNAMIC LOADING

¹ **Mr. Gaurav Tamrakar**

¹ Assistant Professor. Electronics Engineering Department, Kalinga University, Raipur, CG.
gaurav.tamrakar@kalingauniversity.ac.in

² **Mr. Swapnil Shukla**

² Assistant Professor. Mechanical Engineering Department, Kalinga University, Raipur, CG.
swapnil.shukla@kalingauniversity.ac.in

Correspondence author -swapnil.shukla@kalingauniversity.ac.in

ABSTRACT Metal Matrix Composites (MMCs) have emerged as critical structural materials in aerospace, automotive, defence, marine, and high-performance engineering industries due to their superior strength-to-weight ratio, wear resistance, and capability to operate under hostile environments. However, despite extensive research on their static mechanical properties, the behaviour of MMCs under dynamic loading conditions remains a complex and evolving topic. Dynamic loading—such as impact, shock, blast, fatigue, high strain-rate deformation, and cyclic loading—significantly alters material response, dictating deformation mechanisms that differ from quasi-static conditions. This paper provides an integrated review of the mechanical behaviour of MMCs under various dynamic loading regimes, focusing on strain-rate sensitivity, impact toughness, fracture response, thermal–mechanical coupling, and microstructural evolution. Particular attention is given to aluminium, titanium, and magnesium alloy matrices reinforced with ceramic particles (SiC, Al₂O₃, TiC), whiskers, and carbon-based reinforcements. Experimental investigations reported in the literature demonstrate that reinforcement volume fraction, distribution, interfacial bonding, and fabrication route strongly influence the energy absorption and failure patterns of MMCs under dynamic loads. Studies based on Hopkinson Bar tests, drop-weight impact testing, instrumented Charpy tests, ballistic impact assessments, and fatigue loading reveal diverse strain-rate hardening behaviours and failure transitions, ranging from ductile tearing to catastrophic brittle fracture. Furthermore, numerical modelling using FEM, SPH, and multi-scale simulation techniques has been used to predict dynamic deformation with high reliability. The findings collectively highlight that MMCs exhibit significant strain-rate strengthening, enhanced impact resistance, and improved fatigue life when reinforcement dispersion is uniform and interfacial bonding is strong. The paper concludes with gaps in literature, potential advancements in hybrid MMCs, nano-reinforced composites, and additive manufacturing-based MMCs for next-generation dynamic-loading applications.

10.48047/jocaaa.2024.33.07.75

KEYWORDS Metal Matrix Composites (MMCs); Dynamic Loading; Strain-Rate Sensitivity; Impact Behaviour; Fatigue Life; Ballistic Resistance; High-Strain-Rate Testing; Microstructural Evolution; Aluminium Matrix Composites; Ceramic Reinforcements

1. INTRODUCTION

Metal Matrix Composites have become indispensable in modern engineering due to their unique combination of strength, stiffness, and durability, which surpasses conventional monolithic alloys. With rapid technological advancements, many components are subjected to dynamic loading conditions including impact, ballistic penetration, crash events, vibration, cyclic fatigue, and high-strain-rate deformation ($>10^2 \text{ s}^{-1}$). Such loading induces complex stress states and microstructural responses that cannot be predicted using simple static models (Singh & Prasad, 2020). The development of MMCs using liquid metallurgy, powder metallurgy, stir casting, squeeze casting, spray deposition, and additive manufacturing has resulted in composites tailored for dynamic performance. This paper outlines the mechanical behaviour of MMCs subjected to dynamic loads and evaluates the crucial factors influencing their performance.

2. CLASSIFICATION AND CONSTITUENTS OF METAL MATRIX COMPOSITES

MMCs generally consist of metallic matrices such as aluminium, titanium, copper, magnesium, and nickel alloys, reinforced with particles, whiskers, fibres, or hybrid reinforcements. Ceramic particles such as SiC, Al₂O₃, TiC, B₄C, and ZrO₂ are widely used due to their high hardness and thermal stability (Kumar et al., 2021). Reinforcement morphology plays a major role in governing dynamic properties; whiskers and fibres enhance impact resistance and fracture toughness, whereas particles improve stiffness and hardness but may reduce ductility. The interfacial bonding drastically affects load transfer efficiency and crack propagation patterns during high-strain-rate deformation.

3. MANUFACTURING ROUTES AND THEIR EFFECT ON DYNAMIC MECHANICAL PROPERTIES

The fabrication technique significantly influences porosity, reinforcement dispersion, interfacial strength, and grain refinement, all of which govern the response under dynamic loading (Zhao & Li, 2022). Stir casting often results in cost-effective composite production but may introduce clustering and micro-porosity. Powder metallurgy techniques result in homogeneous microstructures with predictable strain-rate sensitivity. Additive manufacturing

10.48047/jocaaa.2024.33.07.75

methods, including SLM (Selective Laser Melting) and DED (Directed Energy Deposition), allow the creation of tailor-made microstructures with enhanced ductility and impact energy absorption due to their refined cellular morphology (Reddy et al., 2023).

4. DYNAMIC LOADING MECHANISMS IN MMCs

Dynamic loading includes sudden or cyclic application of forces that induce high strain rates and non-linear deformation responses. Typical scenarios include high-velocity impacts, ballistic strikes, rotating machinery vibrations, crashworthiness in automobiles, blast wave exposure, and fatigue loading in aerospace structures. These conditions activate alternative deformation mechanisms such as adiabatic shear banding, micro-void coalescence, brittle cleavage, reinforcement–matrix debonding, and thermal instability (Johnson & Sharma, 2019). The strain-rate dependence of MMCs often increases flow stress with increasing strain rate due to limited time for dislocation movement and enhanced dislocation–reinforcement interactions.




Figure 4.1 – Typical Stress–Strain Curve of an MMC under Static and Dynamic Loading

5. EXPERIMENTAL TECHNIQUES FOR DYNAMIC CHARACTERIZATION OF MMCs

10.48047/jocaaa.2024.33.07.75

Dynamic behaviour of MMCs is examined using high-precision experimental techniques, notably Split Hopkinson Pressure Bar (SHPB), drop-weight impact tests, Charpy impact tests, high-speed tensile tests, dynamic fracture toughness tests, and ballistic impact experiments. SHPB provides stress–strain curves at strain rates between 10^2 and 10^4 s^{-1} , revealing rate-dependent strengthening (Rahman et al., 2020). Ballistic impact tests measure energy absorption, penetration resistance, and failure morphology under extreme loads. These tests highlight that reinforcement significantly influences crack propagation and fragmentation patterns.

6. MECHANICAL BEHAVIOUR OF MMCS UNDER HIGH STRAIN RATE LOADING

MMCs generally show strain-rate strengthening, where flow stress increases with the applied strain rate. Aluminium and magnesium matrix composites reinforced with ceramic particles exhibit strain-rate hardening due to dislocation pile-up against reinforcements, increased adiabatic heating, and limited plastic deformation time (Patel & Singh, 2021). Ti-based MMCs show superior dynamic strength due to high interfacial bonding and resistance to crack initiation.

Table 1. Typical Mechanical Properties of Selected MMCs under Dynamic Strain Rates

Composite Type	Reinforcement	Test Type	Strain Rate (s^{-1})	Dynamic Strength Increase (%)
Al-SiC MMC	SiC particles	SHPB	1000	25–40%
Mg- Al_2O_3 MMC	Al_2O_3 fibres	SHPB	1500	30–55%
Ti- B_4C MMC	B_4C particles	Drop-weight	1200	40–60%

Source: Compiled from Rahman et al. (2020), Singh & Prasad (2020), Patel & Singh (2021)

7. IMPACT AND BALLISTIC BEHAVIOUR OF MMCs

Impact behaviour is strongly dependent on reinforcement distribution, matrix ductility, and energy absorption mechanisms. Studies show that MMCs absorb higher impact energy compared to monolithic alloys due to enhanced crack deflection, micro-plasticity, and particle bridging (Mehta & Yadav, 2018). Under ballistic impact, composites with harder

10.48047/jocaaa.2024.33.07.75

reinforcements like B₄C and SiC reduce crater depth and penetration due to localized hardening and rapid crack arrest. Ballistic testing reveals mechanisms such as fragmentation, adiabatic shear failure, plug formation, and petalling.

Table 2. Ballistic and Impact Performance Indicators for Typical MMCs

Composite	Reinforcement %	Impact Energy (J)	Residual Velocity Reduction (%)	Dominant Failure Mode
Al-10% SiC	10% SiC	18–25	35–45%	Ductile tearing + particle cracking
Al-15% B ₄ C	15% B ₄ C	22–30	45–55%	Brittle fracture + shear banding
Mg-8% Al ₂ O ₃	8% Al ₂ O ₃	15–20	25–35%	Matrix cracking + fibre pull-out

8. FATIGUE BEHAVIOUR OF MMCs UNDER CYCLIC DYNAMIC LOADING

Fatigue behaviour is crucial in aerospace, automotive, and marine components subjected to continuous cyclic stresses. MMCs show improved fatigue strength due to their restricted crack initiation and delayed crack propagation (Narayan & Rao, 2022). Reinforcements act as crack barriers, reducing crack tip plasticity. However, improper interfacial bonding may induce early crack initiation. Fatigue life is also sensitive to manufacturing defects, residual stresses, reinforcement clustering, and thermal mismatch stresses. Studies demonstrate a 20–50% increase in fatigue life for optimally reinforced MMCs compared to base alloys.

9. MICROSTRUCTURAL EVOLUTION AND FAILURE MECHANISMS UNDER DYNAMIC LOADS

Dynamic loads trigger non-equilibrium microstructural changes such as adiabatic shear bands, void nucleation, matrix–reinforcement debonding, and grain refinement due to localized heating. High strain rates generate steep thermal gradients that weaken interfacial layers and accelerate dynamic recrystallization (Zhang et al., 2022). Failure mechanisms vary from ductile rupture at low strain rates to brittle cleavage at high strain rates. Reinforcement particles influence crack deflection, branching, and arrest, reducing catastrophic failure. SEM and TEM analyses confirm particle cracking, interfacial decohesion, and shear localization as primary causes of failure during impact and ballistic tests.

10. NUMERICAL AND COMPUTATIONAL MODELLING OF MMCs UNDER DYNAMIC LOADS

Finite Element Modelling (FEM), Smoothed Particle Hydrodynamics (SPH), Cohesive Zone Modelling (CZM), and multi-scale modelling techniques have gained prominence in predicting strain-rate-dependent behaviour of MMCs. FEM simulations incorporate Johnson-Cook constitutive models for dynamic strength prediction (Chen & Wu, 2021). SPH is particularly effective in modelling extreme impact and ballistic events where fragmentation occurs. Micro-mechanical models simulate individual particle–matrix interactions and predict dynamic failure modes. Validated models reduce cost and time associated with experimental testing.

11. RESEARCH GAPS AND FUTURE DIRECTIONS

Despite significant progress, several research gaps remain. Nano-reinforced MMCs, graphene-based hybrid MMCs, and functionally graded composites under dynamic loads require deeper investigation. Additive-manufactured MMCs must be evaluated for long-term fatigue and ballistic performance. More research is needed on high-temperature dynamic behaviour, as most studies only focus on room-temperature conditions. Additionally, multi-scale modelling must be enhanced to accurately simulate interfacial debonding, thermal effects, and crack propagation under extreme strain rates.

12. CONCLUSION

This study demonstrates that MMCs possess outstanding mechanical performance under dynamic loads due to reinforcement-driven strengthening and microstructural stability. Strain-rate sensitivity, impact toughness, ballistic resistance, and fatigue life significantly improve with proper reinforcement selection and optimized processing conditions. The integration of advanced experimental methods with numerical simulations provides comprehensive insights into deformation and failure mechanisms. Overall, MMCs remain highly promising for next-generation engineering applications demanding superior dynamic loading performance.

REFERENCES

1. Ahmed, M., El-Galy, I., & Abd-Elwahed, M. (2019). High strain-rate deformation behavior of SiC-reinforced aluminium composites. *Materials Science and Engineering A*, 759, 339–348.
2. Baroutaji, A., Sajjia, M., & Olabi, A. G. (2018). Impact performance and energy absorption characteristics of metal matrix composites. *Composite Structures*, 187, 528–543.
3. Chauhan, A., & Thakur, R. (2021). Mechanical and dynamic behaviour of hybrid aluminium matrix composites: A review. *Materials Today: Proceedings*, 47, 1342–1354.
4. Dwivedi, S. P., Sharma, S., & Mishra, R. (2020). Influence of reinforcement on impact and wear properties of aluminium metal matrix composites. *Journal of Materials Research and Technology*, 9(6), 14154–14165.
5. Hassan, A. M., & Gupta, M. (2019). Effect of nano-size reinforcements on high strain-rate performance of magnesium alloy composites. *Journal of Magnesium and Alloys*, 7(3), 437–448.
6. Jena, S. K., & Panigrahi, S. K. (2021). Review on ballistic behaviour of aluminium-based metal matrix composites. *Defence Technology*, 18(1), 246–264.
7. Li, X., Zhou, H., & Wang, Y. (2022). Fatigue crack growth behaviour in particle-reinforced aluminium composites under cyclic loading. *Materials Characterization*, 185, 111739.
8. Mani, A., & Prakash, R. V. (2018). Dynamic fracture toughness of aluminium–SiC composites under impact loading. *Engineering Fracture Mechanics*, 191, 187–200.
9. Nassar, A. R., & Elhajjar, R. (2020). Strain-rate sensitivity of titanium metal matrix composites: Experimental and numerical investigation. *International Journal of Mechanical Sciences*, 183, 105791.
10. Pramanik, A. (2017). Effect of machining and surface integrity on fatigue life of metal matrix composites. *Composite Structures*, 168, 98–108.
11. Viswanathan, R., & Perumal, A. (2018). Mechanical behaviour and microstructure of aluminium composites under impact and fatigue conditions. *Materials Today: Proceedings*, 5(11), 23877–23885.
12. Chen, L., & Wu, Y. (2021). Numerical modelling of high-strain-rate deformation in aluminium composites. *Materials Today: Proceedings*, 45, 1201–1210.
13. Johnson, T., & Sharma, H. (2019). Dynamic failure modes in particle-reinforced metal matrix composites. *Composite Structures*, 210, 45–56.

10.48047/jocaaa.2024.33.07.75

14. Kumar, R., Singh, S., & Verma, A. (2021). Role of ceramic reinforcements in aluminium metal matrix composites: A review. *Journal of Composite Materials*, 55(12), 1683–1702.
15. Mehta, V., & Yadav, P. (2018). Impact response of aluminium-based metal matrix composites. *Materials Science Forum*, 940, 215–225.
16. Narayan, R., & Rao, V. (2022). Fatigue behaviour of metal matrix composites: A comprehensive review. *Engineering Fracture Mechanics*, 267, 108235.
17. Patel, P., & Singh, R. (2021). High strain-rate analysis of Al–SiC composites. *Journal of Alloys and Compounds*, 876, 159–172.
18. Rahman, A., Lee, J., & Park, H. (2020). Split Hopkinson pressure bar characterization of magnesium-based metal matrix composites. *Metals*, 10(4), 522.
19. Reddy, K., Zhou, J., & Martin, D. (2023). Additive manufacturing of metal matrix composites and their impact properties. *Additive Manufacturing*, 67, 102345.
20. Singh, A., & Prasad, S. (2020). Mechanical behaviour of metal matrix composites under dynamic loading conditions. *Materials Research Express*, 7(11), 115004.
21. Zhang, W., Li, H., & Zhao, Y. (2022). Microstructural evolution of metal matrix composites under ballistic loading. *International Journal of Impact Engineering*, 169, 103928.